

Dow Corning® MARINE

SILICONE RUBBER SEALANT – ULTIMATE LONG TERM PERFORMANCE

Dow Corning® MARINE is a one part, high performance, flexible silicone sealant specifically formulated for watertight sealing of marine application.

Dow Corning® MARINE has excellent long-term durability, offers high flexibility, good temperature accommodation (-55°C to 150°C) and excellent resistance to salt and fresh water.

PRINCIPAL APPLICATIONS

Dow Corning® MARINE is suitable for the following sealing applications:

- Sealing around hatches and port holes
- Insulating electrical connectors
- Locking nuts and bolts against vibration
- Sealing trunking
- Sealing pipework
- In-situ gaskets for water pumps and exhaust systems
- Creating watertight joints throughout

SPECIFICATIONS

Manufactured under ISO9001



TECHNICAL DATA

Form	Smooth void free viscous paste
Storage Life	Stored below 25°C, in original containers 310ml cartridges - 27 months 78g Injector 12 months
Specific Gravity	1.02
Colours	White, Clear, Black
Base	Acetoxy silicone
Hazardous Ingredients	Non-hazardous
Flammability	Non-flammable
Application Temperature	5°C to 35°C
Temperature Range	-40°C to 150°C
Skin Time	20mins at 23°C and 50% relative humidity
Cure Time	3mm per 24 hours at 23°C and 50% RH.
Hardness	20-25 Shore A
Movement Accommodation Factor	25%
Tensile Strength	2.3 MPa

Specification writers: These values are not intended for use in preparing specifications. Please contact your local **Geocel® Sales Representative** prior to writing specifications on this product.

SURFACE PREPARATION

Ensure all surfaces are clean, dry, sound and free from grease. To obtain good adhesion, clean surfaces with **Geocel® Surface Cleaner** before applying the sealant. Areas adjacent to the joint should be masked with tape to prevent contamination of substrates and ensure a neat sealant line. Where there is a large gap, it is advisable to pack the joint with tissue paper.

APPLICATION

Replace nozzle and cut tip to required width at a 45° angle. Ensure that the adhesive/sealant makes full contact with both sides of the joint. Cut the cartridge nozzle at an angle to ease control of the sealant flow. The nozzle should be cut according to the width of the joint. As the sealant extrudes from the cartridge, draw the cartridge towards you along the joint.

FINISHING

Tooling should be carried out within five minutes of sealing, before a skin forms. This can be achieved by using the back of a spoon. When tooling, it is important to ensure a good contact between the silicone and the substrate. Masking tape should be removed immediately after tooling.

CLEANING

Excess adhesive/sealant may be cleaned off tools, clothing and skin using **Geocel® Eco Cleanse** and **Geocel® Universal Wipes**.

LIMITATIONS

Do not use on substrates that can bleed oils, solvents or plasticisers. Product releases acetic acid during cure, which can corrode sensitive metals such as copper, brass and lead.

PACKAGING

Dow Corning® MARINE is available in both 78g blister card packs packed in boxes of 6, and 310ml cartridges packed in boxes of 12.

ANCILLARY MATERIALS & EQUIPMENT

Cox Powerflow CARTRIDGE Gun

Geocel® Eco Cleanse in 25L Drums

Geocel® Universal Wipes 150 per tub

Geocel® Surface Cleaner in 1L and 5L

HEALTH AND SAFETY

Health and Safety data sheets available on request.

TECHNICAL SERVICE

For further technical information, advice on suitability for specific applications, or detailed Health and Safety information, contact **Geocel® Technical Service**.

IMPORTANT NOTE The information contained herein is offered in good faith and is believed to be accurate. However, because conditions and methods of use of our products are beyond our control, this information should not be used in substitution for customer's tests to ensure that Geocel's products are safe, effective and fully satisfactory for the intended end use. Suggestions of use shall not be taken as inducements to infringe any patent.

Geocel's sole warranty is that the product will meet the Geocel sales specifications in effect at the time of shipment.

Your exclusive remedy for breach of such warranty is limited to refund of purchase price or replacement of any product shown to be other than as warranted.

Geocel specifically disclaims any other express or implied warranty of fitness for a particular purpose or merchantability.

Geocel disclaims liability for any incidental or consequential damage.

Geocel®

Geocel Limited

Western Wood Way, Langage Science Park, Plympton,
Plymouth, Devon, PL7 5BG

Tel: 01752 334350 Fax: 01752 202065

Email: info@geocel.co.uk

www.geocel.co.uk