

Cork Adhesive

Revision: 13/09/2021

Page 1 from 2

Technical data

Basis	(Styrene) Acrylate
Consistency	Paste
Curing system	Physical drying
Density	Ca. 1,50 g/ml
Total solid content	Ca. 78 %
Temperature resistance**	-20°C to +80°C (cured)
Open time (23°C, 55% RV)*	Ca. 20 min.
Application temperature	5 °C → 30 °C
Drying time (23°C and 50% R.H.)	Ca. 12 hours
Consumption*	500 - 600 g/m ²

* These values may vary depending on environmental factors such as temperature, moisture, and type of substrates. ** This information relates to fully cured product.

Product description

Cork Adhesive is a ready to use dispersion adhesive paste for the interior bonding of wall and floor cork.

Properties

- Ready for use paste
- High adhesive strength
- Flexible
- Water resistant
- Not flammable

Applications

- Bonding of cork in wall and floor applications.
- Bonding of rolled cork sheets as insulating backing material.

Packaging

Colour: brown

Packaging: 1 kg plastic pot, 5 kg bucket

Shelf life

At least 12 months in unopened packaging in a dry storage place at temperatures between +5 °C and +25 °C.

Substrates

Substrates: stone, concrete, stucco, wood
Nature: flat, clean, dry, free of dust and grease.
Surface preparation: On very absorbent

surfaces the surface should be treated with a primer.

We recommend a preliminary adhesion test on any substrate.

Application method

Application method: Apply the adhesive by means of a notched trowel (3-5 mm) to the surface. Do not apply more adhesive to the surface as can be covered within 10 min. Roll or press cork very well. After approx. 10 min press or roll edges firmly.

Cleaning: Cork Adhesive may be removed from tools and cork with water. Cured Cork Adhesive can only be removed mechanically.

Repair: With the same material.


Health- and Safety Recommendations

Take the usual labour hygiene into account. Consult label and material safety data sheet for more information.

Remarks

- Remove the cork tiles from their packaging at least 24 hours before installation to allow the tiles to acclimatize.
- Minimum temperature of the substrate should be at least 15°C.
- Never install on a subfloor with too high moisture content.
- After minimum 48 hours, the cork can be further treated (varnished).

Remark: This technical data sheet replaces all previous versions. The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. Since the design, the quality of the substrate and processing conditions are beyond our control, no liability under this publication is accepted. In every case it is recommended to carry out preliminary experiments. Soudal reserves the right to modify products without prior notice.



Cork Adhesive

Revision: 13/09/2021

Page 2 from 2

- First check with your cork supplier if the pre-painted tiles can be bonded with a water based adhesive. If this is not the case, please use Soudal Contact Adhesive 44A.
- Do not dilute the adhesive.

Remark: This technical data sheet replaces all previous versions. The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. Since the design, the quality of the substrate and processing conditions are beyond our control, no liability under this publication is accepted. In every case it is recommended to carry out preliminary experiments. Soudal reserves the right to modify products without prior notice.